



MO-SCI Specialty Products, L.L.C.

A Subsidiary of MO-SCI Corporation

4040 HyPoint North

Rolla, MO 65401

Telephone: 573-364-2338

Fax: 573-364-9589

Silver Coated Glass Microspheres

GL-0279

DATA SHEET

Appearance

Solid soda-lime glass microspheres with metallic silver coating.

Chemical Composition (by weight)

A. Glass

Silica (SiO ₂)	69~72%
Aluminum oxide (Al ₂ O ₃)	1~4%
Calcium oxide (CaO)	9~12%
Magnesium oxide (MgO)	1~3%
Sodium oxide (Na ₂ O).....	13~17%
Iron Oxide (Fe ₂ O ₃)	<0.3%

B. Coating

Silver (Ag).....	~99%
------------------	------

Physical Properties

Specific Gravity	2.5 (g/cm ³)
Bulk Density of Dry Beads.....	1.3 g per cm ³ (77 lbs/ft ³)
Softening Temperature	650°C
Coefficient of Thermal Expansion.	90 x 10 ⁻⁷ /°C (30-300° C)
Approximate Coating Thickness.....	600-1000 angstroms

Applications:

Typical applications of GL0279 beads including: conductive filler for plastic, pigment, and etc...

